

Product Description

Dycotec DM-CUP-5054 copper paste is designed for rotary and flat-bed screen printing for versatile use in electronic applications. The paste is designed to be rapidly cured using Xenon flash and laser systems.

Product Benefits

- Excellent electrical conductivity
- Good adhesion
- Compatibility with a broad range of light based sintering techniques

Paste Preparation

Gently stir the paste before use to ensure the product is well mixed. Be careful not to introduce air bubbles. Do not replace used ink in the container. This ink is designed for screen printing processes. Once printed, the paste should be dried at 60-80°C.

Properties of the Uncured Paste

Test	Properties
Solids	77-81%
Viscosity (50 s ⁻¹ , cone & plate)	10-20 Pa.s at 25°C
Thinner	For slight adjustments in viscosity use DM-CUP-5054-DT
Substrate compatibility	Polyimide, paper, glass*
Typical Print Thickness	15 µm
Coverage	160 cm ² /g at 10 µm cured print thickness

*Requires increased power density from laser/flash lamp system

Paste Processing Conditions

Test	Typical Properties
Screen	325 SS mesh, 13 µm emulsion
Squeegee Type	80A Shore
Line/Space (µm)	100/125
Print Speed	30-70 mm/s
Drying Temperature/Time	60-80°C for 20 mins

Clean-Up

Equipment can be cleaned using benzyl alcohol or IPA

Paste Curing Conditions

It is recommended that printed structures should be laser or flash lamp processed shortly after drying.

Test	Properties
Sintering Technique Compatibility	Flash lamp, Laser

Properties of the Cured Paste

Test	Properties
Adhesion	4B for PI
Volume Resistivity	35 $\mu\Omega$.cm
Resistivity	15 m Ω /□/ mil for polyimide

Storage and Shelf-life

Containers should be stored in a fridge with lids tightly sealed. We cannot assume responsibility for an ink that has not been stored in appropriate conditions or where the ink has been contaminated following use. Please ensure the paste is removed from the fridge and left to stand to ensure paste temperature is greater than 15°C prior to use.

Safety and Handling

For safe use of this product, please review relevant material and safety datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd
Unit 12, Star West
Westmead, Westlea
Swindon, Wiltshire
SN5 7SW UK
Email: info@dycotecmaterials.com
Tel: +44 (0)1793 422598
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.