

Product Description

Dycotec DM-CAP-4511S is a thermoplastic carbon paste for flat-bed screen printing. The paste allows fast drying at low temperature (120°C for 10 mins) with a sheet resistance of 15 $\Omega/\square/25\mu\text{m}$ capable of printing 100 μm line widths.

Product Benefits

- Print resolution to 100 μm line widths
- Good flexibility
- Low temperature drying
- Compatibility with low temperature substrates such as PET

Paste Preparation

Gently stir before use. Avoid rapid stirring to prevent air entrapment during the stirring process. Once the paste has been removed from the container for printing, this may introduce contamination. Please do not replace the paste in the original container and keep the lids tightly sealed with the inner cap after paste transfer to minimise solvent evaporation.

Properties of the Uncured Paste

| Test | Typical Properties |
|--|---|
| Viscosity (Pa.S) (Lamy, Cone & plate, 50s ⁻¹ , 25°C) | 5 - 8 Pa.s |
| Thinner | This should normally not be required. If necessary, use DM-CAP-4500-DT for slight adjustments in viscosity. |
| Coverage | 150 cm ² /g at 9-12 μm dried print thickness |

Paste Processing Conditions

| Parameter | Typical Properties |
|-----------------------|--------------------------------------|
| Substrate | PET, glass |
| Deposition Method | Flat-bed screen printing |
| Screen | 180 SS, 13 μm emulsion |
| Flood Speed | 50 mm/s |
| Print Speed | 45 mm/s |
| Squeegee hardness | 70 Durometer Shore A |
| Squeegee angle | 60° |
| Squeegee pressure | 5 Kg at a squeegee length of 22.2 cm |
| Print gap | 0.75 mm |
| Number of strokes | 1 |
| Screen Residence Time | >20 mins |
| Print Resolution | 100 μm |

Print structures should be processed at 120°C in a convection oven for 10 mins

Properties of the Cured Paste

| Test | Properties |
|------------------------------------|---|
| HALT Durability Tests | No resistance change after 1000 hrs tests at 85°C/85% RH |
| Sheet Resistance | 15 Ω/\square /25 μm |
| Adhesion | 5B |
| Pencil hardness scale | 2B |
| Flexibility (ASTM F1683, 5 cycles) | No resistance change (40mm diam. tube) >250 μm width |

Clean-Up

Equipment can be cleaned using alcohols such as iso-propanol or acetone.

Storage and Shelf-life

Containers should be stored at room temperature (10 – 25°C) with lids tightly sealed. The material should not be stirred at temperature below 0°C or greater than 25°C. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

Safety and Handling

For safe use of this product, please review relevant material safety and datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd
Unit 12, Star West
Westmead Industrial Estate
Swindon SN5 7SW
Wiltshire, UK
Email: info@dycotecmaterials.com
Tel: +44 (0)1793 422598
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up. More detailed information can be obtained via info@dycotecmaterials.com.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Materials' products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a licence under any Dycotec Materials' patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more UK or foreign patents or patent applications.