

Product Description

Dycotec DM-AS-10002S is a silver epoxy based conductive adhesive that is used for thin film PV, sensors and general printed electronics applications. The paste is compatible with manual and syringe application.

Product Benefits

- Solvent free
- Excellent electrical conductivity
- Good joint strength
- Compatible with a range of deposition processes
- High mechanical hardness

Paste Preparation

DM-AS-10002S is a two part silver epoxy based conductive adhesive system. It requires mixing of the Part B, DM-AS-10002B and the Part A, DM-AS-10002A in the correct ratios to form the DM-AS-10002S paste. The contents of one container of the Part B, DM-AS-10002B system must be added completely to a pot of DM-AS-10002A. The combined pastes should then be mixed slowly. Avoid rapid stirring to prevent air entrapment during the stirring process. As soon as the product is activated, the material should be used immediately.

Properties of Uncured Paste

Test	Properties
Pot life	>30 mins
Solids Content	88-92 %
Solvent	None

Paste Processing Conditions

The paste can be dried using either a convection oven, IR heating or a hot gun. Typical drying parameters used are 140°C for 60 mins for a convection oven and 1-2 mins for hot air gun processing. Drying times may be reduced to achieve the optimum resistivity depending on manufacturing process set-up.

Properties of Cured Paste

Test	Properties
Sheet Resistance	<250 mΩ/□/mil (140°C, 60 mins)
Volume Resistivity	<0.0006 Ω.cm (140°C, 60 mins)
Pull Strength (ASTMD4541-02)	>8 Kg/cm ²
Pencil Hardness	8H

Clean-Up

Equipment can be cleaned using isopropanol alcohol or acetone.

Storage and shelf-life

Containers should be stored at room temperature with lids tightly sealed. The paste shelf-life for an unopened container is 6 months from date of shipment. Avoid introduction of water into the paste. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

Safety and Handling

For safe use of this product, please review relevant material safety and datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd

Unit 12, Star West

Westmead Industrial Estate

Swindon, Wiltshire UK

Email: Info@dycotecmaterials.com

Tel: +44 (0)1793 422598

www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.