

## Product Description

Dycotec DM-OC-6030S is a thermally cured paste for screen printing for use with conductive transparent overcoat DM-SNW-8010S.

## Product Benefits

- Formulated for screen printing
- Excellent transparency
- Protective overcoat for Dycotec's transparent conductive pastes (DM-SNW-8010S)
- Excellent printability
- Low temperature cure

## Paste Preparation

DM-OC-6030S is a single part paste system. Once the paste has been removed from the container for printing, this may introduce contamination. Please do not replace the paste in the container. The paste should be gently stirred before use avoiding incorporation of air bubbles. Avoid paste drying on screen, use flood-print-flood process to avoid drying.

## Properties of the Uncured Paste

Test	Properties
Viscosity after mixing (Pa.s) (Lamy, cone and plate 50s <sup>-1</sup> , 20°C)	10 - 15
Colour	Clear
Density (g/cm <sup>3</sup> )	1.1
Solids Content	20%
Thinner	DM-OC-6030-DT

## Paste Processing Conditions

Parameter	Typical Properties
Substrate	PET
Screen	325 SS, 23 µm EOM or P120/31 polyester, 21 µm EOM
Screen residence time	>1 hour
Flood speed	70 mm/s
Print speed	70 mm/s
Squeegee type	80 durometer (Red)
Curing temperature	80-100°C
Curing time	10-20 mins

The paste can be dried using either a convection oven or IR heating. Typical drying parameters used are 80°C-100°C for 10-20 mins. Drying times may be reduced to achieve the optimum production rate depending on manufacturing process set-up

## Properties of the Cured Paste

Test	Properties
Adhesion	5B
Transparency	>99%

## Clean-Up

Equipment can be cleaned using solvents such as PGMEA (Propylene glycol methyl ether acetate)

## Storage and Shelf-life

Store at room temperature (10-25°C) with lids tightly sealed. The paste shelf-life for an unopened container is 12 months from date of shipment. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

## Safety and Handling

For safe use of this product, please review relevant material safety and datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd  
Unit 6, Stainer Road  
Calne  
Wiltshire  
SN11 9PX UK  
Email: [info@dycotecmaterials.com](mailto:info@dycotecmaterials.com)  
Tel: +44 (0)1793 422598  
[www.dycotecmaterials.com](http://www.dycotecmaterials.com)

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.