

Product Description

DM-CAP-4101S is a single part screen printable thermoset carbon paste that is resistant to solvents such as MEK (Methyl Ethyl Ketone). It offers exceptional levels of hardness(5H) and electrical conductivity($10\Omega/\text{sqr}/25\mu\text{m}$). Typical applications include; EMI/RFI shielding of flexible substrates, polymer thick film circuitry, potentiometers, membrane switches and printed resistors.

Product Benefits

- Excellent hardness (5H)
- Excellent resistance to solvents including MEK (Methyl Ethyl Ketone)
- Excellent conductivity ($10\Omega/\text{sqr}/25\mu\text{m}$ at 200°C cure)
- Single part system with excellent printability
- Paste systems at variable sheet resistance available: 100, 1000 and 10,000 $\Omega/\text{sqr}/25\mu\text{m}$

Paste Preparation

The paste is a single part system. Gently stir before use. Avoid rapid stirring to prevent air entrapment during the stirring process. Once the paste has been removed from the container for printing, this may introduce contamination. Please do not put used paste back into the original container.

Properties of Uncured Paste

Test	Properties
Viscosity (Malvern, cone-plate 50s ⁻¹ , 25°C)	5,000-10,000 cP
Thinner	This should normally not be required. If necessary, use DM-CAP-4101S-DT for slight adjustments in viscosity.
Coverage	200 cm ² /g for 25 μm thickness
Colour	Black

Paste Processing Conditions

Parameter	Typical Properties
Substrate	Glass, FR4, Polyimide
Screen	180 mesh count / inch SS, 13 μm emulsion
Squeegee hardness	80 Durometer Shore A
Print Mode	Flood/Print
Print Speed	70 to 450 mm/s
Squeegee pressure	5 kg over 22cm
Print gap	1.2 mm
Cured thickness	~29 μm
Screen Residence Time	>1 hr

Guideline curing parameters are 150°C-200°C- for 30 – 60 mins in a well ventilated convection oven.

Properties of Cured Paste

Test	Typical Properties
Sheet Resistance (ASTM D257)	<10 $\Omega/\square/25\mu\text{m}$ (200°C cure), <20 $\Omega/\square/25\mu\text{m}$ (150°C cure)
Adhesion (ASTM D3359)	5B
Pencil hardness (ASTM D3363)	5H
MEK Resistance (ASTM D4752)	No paste removed, clean wipe
Surface Roughness, R_a (based on ASTM D7127)	<1 μm

Clean-Up

Equipment can be cleaned using alcohols such as IPA or acetone.

Storage and shelf-life

Containers should be stored at room temperature (10 – 20°C) with lids tightly sealed. The paste shelf-life for an unopened container is 3 months from date of shipment. The material should not be stored at temperature below 0°C or greater than 25°C. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

Safety and Handling

For safe use of this product, please review relevant material and safety datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd
Unit 6, Stainer Road
PorteMarsh Industrial Estate
Calne SN11 9PX
Wiltshire, UK
Email: info@dycotecmaterials.com
Tel: +44 (0)1793 422598
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up. More detailed information can be obtained via info@dycotecmaterials.com.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Materials' products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a licence under any Dycotec Materials' patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.