

Product Description

Dycotec Materials DM-INS-2520 is a screen printable insulator coating that is used in stretchable applications such as wearable devices, sensors and medical devices. The paste can be applied to elastomeric and textile substrates. The paste is cured at temperatures between 120-150°C.

Product Benefits

- Translucent
- Stretchable >50%
- Compatible with a wide variety of substrates including TPU, textiles, PET

Paste Preparation

DM-INS-2520 is a single part paste system. Once the paste has been removed from the container for printing, this may introduce contamination. Please do not replace the paste in the container. The paste should be gently stirred before use avoiding incorporation of air bubbles. Avoid paste drying on screen, use flood-print-flood process to avoid drying.

Properties of the Uncured Paste

Test	Properties
Viscosity after mixing (Pa.s) (Cone and plate 50s ⁻¹ , 20°C)	2 - 5
Density (g/cm ³)	~1.1
Thinner	For slight adjustments in viscosity, use DM-INS-2520-DT
Solids Content	17-22 %

Paste Processing Conditions

Parameter	Typical Properties
Substrate	TPU, Textiles, elastomers
Screen	180 SS, 25 µm emulsion
Print speed	70 mm/s
Squeegee type	80A Shore
Surface Area Coverage	190 cm ² /g at 10 µm thickness
Print Method	Print and Flood
Screen Residence Time	>4 hours
Print Thickness	7 - 10 µm

The paste can be dried using either a convection oven or IR heating. Typical curing parameters used are 120°C-150°C for 10-30 mins. Drying times may be reduced to achieve the optimum resistivity depending on manufacturing process set-up.

Properties of the Cured Paste

Test	Properties
Adhesion	5B
Mechanical hardness	2B - 5B
Damp Heat Test (85/85)	1000 hrs
Stretchability	~50%

Conductive Layers

Please contact Dycotec Materials regarding suitable stretchable conductive layers for your application.

Clean-Up

Equipment can be cleaned using benzyl alcohol then wipe dry with isopropanol.

Storage and Shelf-life

For optimum results, the containers should be stored in a cool dry place with lids tightly sealed. The paste shelf-life for an unopened container is 6 months from date of shipment. Avoid introduction of contaminants into the paste. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

Safety and Handling

For safe use of this product, please review relevant material safety and datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd
Unit 6, Stainer Road
Porte Marsh Industrial Estate
Calne, Wiltshire, SN11 9PX, UK
Email: info@dycotecmaterials.com
Tel: +44 (0)1793 422596
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.