

Product Description

DM-SIP-1006 is part of the Dycotec Materials product portfolio developed specifically for In-Mold Electronics (IME) applications. It is a solvent based screen printable conductive ink used to produce highly electrically conductive structures used in multilayer circuit designs. The paste is compatible with thermoforming processes and overmolding temperatures.

Product Benefits

- Good thermoformable characteristics for In-Mold Electronics (IME) use
- Excellent printability
- Excellent electrical conductivity (15 mΩ/□/25μm)
- Compatible with Dycotec Materials IME dielectric and conductive adhesive pastes

Paste Preparation

DM-SIP-1006 is a thermoplastic silver paste system. Once the paste has been removed from the container for printing, this may introduce contamination. Please do not replace the paste in the container. The paste should be gently stirred before use avoiding incorporation of air bubbles.

Properties of Uncured Paste

Test	Properties
Viscosity after mixing (Pa.s) (Cone and plate 50s ⁻¹ , 20°C)	6 - 10
Density	2.2 g/cm ³
Colour	Silver
Thinner	DM-SIP-1006-DT
Solids Content	65-70 %

Paste Processing Conditions

Parameter	Typical Properties
Substrate	Polycarbonate
Screen	280SS, 10 μm EOM or 325SS, 13 μm EOM
Print speed	100 - 400 mm/s
Squeegee type	80A Shore
Print Resolution	250 μm (line and gap)
Coverage	156 cm ² /g (10 μm thickness)

The paste can be dried using either a convection oven or using IR heating. Typical drying parameters used are 80°C followed by 120-130°C for 5-20 mins. Drying times may be reduced to achieve the optimum resistivity depending on manufacturing process set-up.

Properties of Cured Paste

Test	Typical Properties
Sheet Resistance	15 m Ω /□/25 μ m
Elongation	30%
Adhesion (ASTM D3359)	5B, no removal
Environmental (85°C/85%RH,1000hrs)	No increase in sheet resistance

Clean-Up

Equipment can be cleaned using benzyl alcohol followed by iso-propanol, wipe dry.

Storage and shelf-life

Containers should be stored in a fridge at a temperature between 4-7°C with lids tightly sealed. The paste shelf-life for an unopened container is 3 months from date of shipment. Please ensure the material has time to reach room temperature before use. Avoid introduction of water into the paste. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

Safety and Handling

For safe use of this product, please review relevant material safety and datasheet (MSDS).

For more information, please contact:

Dycotec Materials Ltd
Unit 6, Stainer Road
Porte Marsh Industrial Estate
Calne, Wiltshire, SN119PX, UK
Email: Info@dycotecmaterials.com
Tel: +44 (0)1793 422596
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.