

Product Description

DM-TIM-15323 is a high thermal conductivity single part epoxy adhesive. It is designed to provide superior heat transfer between a heat generating component eg power device and heat sink, heat spreader or other cooling device eg fans, heat pipes whilst ensuring high voltage isolation. The materials act as both a thermal interface material and an adhesive reducing the amount of assembly components needed in a device.

Product Benefits

- Excellent thermal conductivity (2.3 W/m.K)
- High bond strength
- High breakdown voltage >10 kV/mm
- Single part system
- Excellent thermal stability with high operating temperatures
- Low water absorption

Applications

- Heat sink bonding
- Potting/encapsulating sensors
- Semiconductor use eg chip-scale packages, power semiconductors
- Battery systems - modules and packs
- LED and Automotive lighting
- Power supplies
- Industrial appliances

Physical Properties

Test	Properties
Viscosity before Phase Change (Pa.s) (Lamy Cone & Plate, 50s ⁻¹ , 25°C)	40-60
Density (ASTM D792)	2.5 g/cm ³
Colour	Grey

Deposition/Cure Properties

Syringe	Properties
Recommended Drying Conditions	150°C (30 mins)
Substrates	Plastics, ceramics, aluminium, copper, glass
Dispense Method	Pressure-time dispense from syringe

Thermal/Electrical Properties

Parameter	Properties
Thermal Conductivity (ASTM D5470)	2.3 W/m.K
Hardness (ASTM D5470)	>90 (Shore D)
Glass Transition Temperature (T _g)	130°C
Lap Shear Strength (Aluminium)	2580 psi
Thermal Contact Resistance (ASTM D5470)	7 x 10 ⁻⁵ m ² .K/W
Volume Resistivity (ASTM D257)	>1 x 10 ¹² Ω.cm
Dielectric Constant (1 KHz) (ASTM D149)	9.7
Dielectric Strength (ASTM D149 MOD)	>10 kV/mm
Weight Loss (TGA)	0.06% (250°C), 0.34% (300°C), 3% (350°C)
Water Absorption (ASTM D570-98)	0.1%

Durability Performance

Parameter	Properties
Thermal Stability (150°C, bake test)	1000 hours
Highly Accelerated Lifetime Testing	1000 hours (85°C, 85% RH)
Operating Temperature Range	200°C

The product is RoSH compliant.

Storage and shelf-life

The paste shelf-life is 6 months from date of shipment. Please store pastes at refrigerated temperatures (4-7°C).

Safety and Handling

For safe use of this product, please review relevant material and safety datasheet (MSDS).

Packaging

Package sizes of 10cc manual syringe application. Other syringe types/sizes and pots available on request.

For more information, please contact:

Dycotec Materials Ltd
Unit 6, Stanier Road
Porte Marsh Industrial Estate
Calne, Wiltshire, SN11 9PX, UK
Email: Info@dycotecmaterials.com
Tel: +44 (0)1793 422598
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up. Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.